

# Core 201LN/4372

## General characteristics

This low-nickel stainless steel also has properties approaching Core 301/4310, but has a higher strength than Core 201/4372. It hardens more quickly due to its higher work hardening coefficient.

## Typical applications

- Railroad freight cars
- Truck trailers
- Coal handling
- Bulk transport equipment

## Products & dimensions

### Cold rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
2B	Cold rolled, heat treated, pickled, skin passed	0.63-3.57	914-1524	0.63-3.57	914-1524
2D	Cold rolled, heat treated, pickled	0.63-2.78	914-1524	0.63-2.78	914-1524
2K	Satin finish	0.63-3.05	914-1524	0.63-3.05	914-1524

### Continuous hot rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
1D	Hot rolled, heat treated, pickled	2.54-9.52	914-1219	2.54-9.52	914-1219

## Chemical composition

The typical chemical composition for this grade is given in the table below, together with composition limits given for the product according to different standards. The required standard will be fully met as specified on the order.

The chemical composition is given as % by mass.

	C	Mn	Cr	Ni	Mo	N	Other
Typical	0.02	6.6	16.2	4.1		0.16	Cu:0.75

# Corrosion resistance

Pitting corrosion resistance		Crevice corrosion resistance
PRE	CPT	CCT
19		

Pitting Resistance Equivalent (PRE) is calculated using the following formula:  $PRE = \%Cr + 3.3 \times \%Mo + 16 \times \%N$

Corrosion Pitting Temperature (CPT) as measured in the Avesta Cell (ASTM G 150), in a 1M NaCl solution (35,000 ppm or mg/l chloride ions).

Critical Crevice Corrosion Temperature (CCT) is obtained by laboratory tests according to ASTM G 48 Method F

## Mechanical properties

## Physical properties

Density	Modulus of elasticity	Thermal exp. at 100 °C	Thermal conductivity	Thermal capacity	Electrical resistance	Magnetizable
kg/dm <sup>3</sup>	GPa	10 <sup>-6</sup> /°C	W/m°C	J/kg°C	μΩm	
7.8	200		15		0.7	No

## Fabrication

More detailed information concerning welding procedures can be obtained from the Outokumpu Welding Handbook, available from our sales offices.

## Standards & approvals

Standard	Designation
----------	-------------

## Contacts & Enquiries

Contact your nearest sales office

[www.outokumpu.com/contacts](http://www.outokumpu.com/contacts)

# Working towards forever.

We work with our customers and partners to create long lasting solutions for the tools of modern life and the world's most critical problems: Clean energy, clean water and efficient infrastructure. Because we believe in a world that lasts forever.

Information given in this brochure may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but Outokumpu and its affiliated companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and Outokumpu and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability



[outokumpu.com](http://outokumpu.com)  
[steelfinder.outokumpu.com](http://steelfinder.outokumpu.com)