

Forta 430/4016

EN 1.4016, ASTM TYPE 430 / UNS S43000

General characteristics

Forta 430/4016 is a classic 16% chromium ferritic stainless steel for mildly corrosive environments. Not recommended for welding due to its decreased intergranular corrosion resistance

Typical applications

- Tanks
- Cutlery
- Household appliances

Products & dimensions

Cold rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
2A	2A	0.50-1.00	35-1280	0.50-1.00	35-1280
2B	Cold rolled, heat treated, pickled, skin passed	0.30-5.00	12-1550	0.30-5.00	18-1550
2BB	Bright-pickled	0.25-3.50	30-1524	0.25-3.50	35-1300
2C	Cold rolled, heat treated	0.80-5.00	30-1530		
2E	Cold rolled, heat treated, mech. desc. pickled	0.33-5.00	12-1530	0.33-5.00	18-1530
2F	Cold rolled, heat treated, skin passed	0.33-3.58	12-1524	0.33-3.58	18-1524
2G	Ground	0.40-3.58	12-1530	0.40-3.58	18-1530
2H	Work hardened	0.05-5.00	3-1530	0.30-5.00	18-1530
2J	Brushed or dull polished	0.40-3.00	30-1530	0.40-3.00	35-1530
2K	Satin finish	0.53-3.58	12-1530	0.53-3.58	18-1530
2M	Patterned	0.40-3.50	30-1524	0.40-3.50	600-1500
2R	Cold rolled, bright annealed	0.05-3.00	3-1500	0.20-3.00	18-1500

Continuous hot rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
1C	Hot rolled, heat treated, not descaled	2.00-8.00	50-1530		

1D	Hot rolled, heat treated, pickled	2.50-8.00	50-1524	2.50-8.00	350-1524
1E	Hot rolled, heat treated, mech. desc.	1.50-3.00	50-1530	1.50-3.00	50-1530
1G	Ground	2.00-3.00	750-1455	2.00-3.00	750-1455
1H	Hot rolled, temper rolled	2.00-2.50	35-1550		
1M	Patterned	2.00-3.00	750-1455	2.00-3.00	750-1455
1U	Black hot rolled	2.00-8.00	50-1550		

Chemical composition

The typical chemical composition for this grade is given in the table below, together with composition limits given for the product according to different standards. The required standard will be fully met as specified on the order.

The chemical composition is given as % by mass.

	C	Mn	Cr	Ni	Mo	N	Other
Typical	0.05		16.2				
ASME II A SA-240	≤0.12	≤1.00	16.0-18.0	≤0.75			
ASTM A240	≤0.12	≤1.00	16.0-18.0	≤0.75			
EN 10088-2	≤0.08	≤1.0	16.0-18.0				
EN 10088-3	≤0.08	≤1.00	16.0-18.0				
EN 10088-4	≤0.08	≤1.0	16.0-18.0				
IS 6911	≤0.12	≤1.00	16.0-18.0	≤0.75	≤0.30		

Corrosion resistance

Pitting corrosion resistance		Crevice corrosion resistance
PRE	CPT	CCT
16	<10	<0

Pitting Resistance Equivalent (PRE) is calculated using the following formula: $PRE = \%Cr + 3.3 \times \%Mo + 16 \times \%N$

Corrosion Pitting Temperature (CPT) as measured in the Avesta Cell (ASTM G 150), in a 1M NaCl solution (35,000 ppm or mg/l chloride ions).

Critical Crevice Corrosion Temperature (CCT) is obtained by laboratory tests according to ASTM G 48 Method F

Mechanical properties

Cold rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 1 mm)	365	390	520	50				
ASME II A SA-240	≥ 205		≥ 450				≤ 183	
ASTM A240	≥ 205		≥ 450			≤ 89HRB	≤ 183	
EN 10088-2	≥ 260		430 - 600	≥ 20				
EN 10088-4								
IS 6911	≥ 205		≥ 450			≤ 89HRB	≤ 183	

Hot rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
---------------------------	--------------------------	--------------------------	-----------------------	-------------------------------	----------------------	----------	----	----

Typical (thickness 4 mm)	370	395	515	21			80	
ASME II A SA-240	≥ 205		≥ 450				≤ 183	
ASTM A240	≥ 205		≥ 450				≤ 183	
EN 10088-2	≥ 240		430 - 600	≥ 18				
EN 10088-4								
IS 6911	≥ 205		≥ 450			≤ 89HRB	≤ 183	

Hot rolled quarto plate	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 15 mm)	365		505	20				
ASME II A SA-240	≥ 205		≥ 450				≤ 183	
ASTM A240	≥ 205		≥ 450				≤ 183	
EN 10088-2	≥ 260		430 - 630	≥ 20				
EN 10088-4	≥ 260		430 - 630					
IS 6911	≥ 205		≥ 450			≤ 89HRB	≤ 183	

Wire rod	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical	280		450	25				

¹⁾Elongation according to EN standard:

A₈₀ for thickness below 3 mm.

A for thickness = 3 mm.

Elongation according to ASTM standard A₂ or A₅₀.

Physical properties

Data according to EN 10088

Density	Modulus of elasticity	Thermal exp. at 100 °C	Thermal conductivity	Thermal capacity	Electrical resistance	Magnetizable
kg/dm ³	GPa	10 ⁻⁶ /°C	W/m°C	J/kg°C	μΩm	
7.7	220	10	25	460	0.60	Yes

Fabrication

Standards & approvals

The most commonly used international product standards are given in the table below.

Standard	Designation
ASME SA-240M Code Sect. II. Part A	TYPE 430 / UNS S43000
ASTM A240/A240M	TYPE 430 / UNS S43000
EN 10088-2	1.4016
EN 10088-3	1.4016

Contacts & Enquiries

Contact your nearest sales office

www.outokumpu.com/contacts

Working towards forever.

We work with our customers and partners to create long lasting solutions for the tools of modern life and the world's most critical problems: Clean energy, clean water and efficient infrastructure. Because we believe in a world that lasts forever.

Information given in this brochure may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but Outokumpu and its affiliated companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and Outokumpu and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability



outokumpu.com
steelfinder.outokumpu.com