

Forta 301/4310

EN 1.4310, ASTM TYPE 301 / UNS S30100

General characteristics

Forta 301/4310 is a lower chromium and nickel variant of Core 304/4301 with high work hardening capacity. Used for items subject to high mechanical loading.

Typical applications

- Springs
- Press plates
- Conveyor chains
- Mixer blades
- Automotive cylinders and head gaskets

Products & dimensions

Cold rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
2B	Cold rolled, heat treated, pickled, skin passed	0.33-6.35	12-1550	0.33-6.35	18-1550
2BB	Bright-pickled	0.30-3.50	30-1530	0.30-3.50	600-1530
2C	Cold rolled, heat treated	0.50-6.00	30-1530		
2D	Cold rolled, heat treated, pickled	0.30-6.35	30-1590	0.30-6.35	400-1590
2E	Cold rolled, heat treated, mech. desc. pickled	0.30-6.00	12-1530	0.33-6.00	18-1530
2F	Cold rolled, heat treated, skin passed	0.33-3.58	12-1524	0.33-3.58	18-1524
2G	Ground	0.30-3.58	12-1530	0.30-3.58	18-1530
2H	Work hardened	0.05-22.00	3-1500	0.30-5.00	18-1500
2J	Brushed or dull polished	0.30-3.00	30-1500	0.30-3.00	600-1530
2K	Satin finish	0.53-3.58	12-1524	0.53-3.58	18-1524
2R	Cold rolled, bright annealed	0.05-3.50	3-1500	0.33-3.50	18-1500

Continuous hot rolled products, available dimensions (mm)

Surface finish		Coil / Strip		Plate / Sheet	
		Thickness	Width	Thickness	Width
1C	Hot rolled, heat treated, not descaled	2.00-10.00	50-1550		

1D	Hot rolled, heat treated, pickled	2.54-9.52	50-1610	2.54-9.52	50-1610
1E	Hot rolled, heat treated, mech. desc.	1.75-4.50	50-1610	1.75-4.50	50-1610
1G	Ground	2.00-3.00	750-1350	2.00-3.00	750-1350
1U	Black hot rolled	2.00-10.00	50-1550		

Chemical composition

The typical chemical composition for this grade is given in the table below, together with composition limits given for the product according to different standards. The required standard will be fully met as specified on the order.

The chemical composition is given as % by mass.

	C	Mn	Cr	Ni	Mo	N	Other
Typical	0.10		17.0	7.0			
ASME II A SA-240	≤0.15	≤2.00	16.0-18.0	6.0-8.0		≤0.10	
ASME II A SA-240	≤0.03	≤2.00	16.0-18.0	6.0-8.0		≤0.20	
ASTM A240	≤0.15	≤2.00	16.0-18.0	6.0-8.0		≤0.10	
ASTM A240	≤0.03	≤2.00	16.0-18.0	6.0-8.0		≤0.20	
ASTM A666	≤0.15	≤2.00	16.0-18.0	6.0-8.0		≤0.10	
EN 10088-2	0.05-0.15	≤2.0	16.0-19.0	6.0-9.5	≤0.80	≤0.10	
EN 10088-3	0.05-0.15	≤2.00	16.0-19.0	6.0-9.5	≤0.80	≤0.10	
IS 6911	≤0.15	≤2.00	16.0-18.0	6.0-8.0	≤0.70	≤0.10	
IS 6911	≤0.03	≤2.00	16.0-18.0	6.0-8.0	≤0.70	≤0.20	

Corrosion resistance

Pitting corrosion resistance		Crevice corrosion resistance
PRE	CPT	CCT
17	<10	<0

Pitting Resistance Equivalent (PRE) is calculated using the following formula: $PRE = \%Cr + 3.3 \times \%Mo + 16 \times \%N$
Corrosion Pitting Temperature (CPT) as measured in the Avesta Cell (ASTM G 150), in a 1M NaCl solution (35,000 ppm or mg/l chloride ions).

Critical Crevice Corrosion Temperature (CCT) is obtained by laboratory tests according to ASTM G 48 Method F

Mechanical properties

Cold rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 1 mm)	300	325	770	65				
ASME II A SA-240	≥ 205		≥ 515				≤ 201	
ASME II A SA-240	≥ 220		≥ 550					
ASTM A240	≥ 205		≥ 515			≤ 95HRB	≤ 201	
ASTM A240	≥ 220		≥ 550					
EN 10088-2	≥ 250	≥ 280	600 - 950	≥ 40				
IS 6911	≥ 205		≥ 515			≤ 95HRB	≤ 217	
IS 6911	≥ 220		≥ 550			≤ 100HRB	≤ 241	

Hot rolled coil and sheet	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 4 mm)	330	365	750	50			90	
ASME II A SA-240	≥ 205		≥ 515				≤ 201	
ASME II A SA-240	≥ 220		≥ 550					
ASTM A240	≥ 205		≥ 515				≤ 201	
ASTM A240	≥ 220		≥ 550					
IS 6911	≥ 205		≥ 515			≤ 95HRB	≤ 217	
IS 6911	≥ 220		≥ 550			≤ 100HRB	≤ 241	

Hot rolled quarto plate	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical (thickness 15 mm)	285	315	785					
ASME II A SA-240	≥ 205		≥ 515				≤ 201	
ASME II A SA-240	≥ 220		≥ 550					
ASTM A240	≥ 205		≥ 515				≤ 201	
ASTM A240	≥ 220		≥ 550					
IS 6911	≥ 205		≥ 515			≤ 95HRB	≤ 217	
IS 6911	≥ 220		≥ 550			≤ 100HRB	≤ 241	

Wire rod	R _{p0.2} MPa	R _{p1.0} MPa	R _m MPa	Elongation ¹⁾ %	Impact strength J	Rockwell	HB	HV
Typical	300	330	800	50				

¹⁾Elongation according to EN standard:

A_{g0} for thickness below 3 mm.

A for thickness = 3 mm.

Elongation according to ASTM standard A₂ or A₅₀.

Physical properties

Data according to EN 10088 is shown in the table below.

Density	Modulus of elasticity	Thermal exp. at 100 °C	Thermal conductivity	Thermal capacity	Electrical resistance	Magnetizable
kg/dm ³	GPa	10 ⁻⁶ /°C	W/m°C	J/kg°C	μΩm	
7.9	200	18,0	15	500	0.73	No

Fabrication

Standards & approvals

Standard	Designation
ASME SA-240M Code Sect. II. Part A	TYPE 301L / UNS S30103; TYPE 301L / UNS S30103
ASTM A240/A240M	TYPE 301L / UNS S30103; TYPE 301L / UNS S30103

ASTM A666	TYPE 301L / UNS S30103
EN 10088-2	1.4310
EN 10088-3	1.4310
IS 6911, AMENDMENT NO. 2	ISS 301; ISS 301L

Contacts & Enquiries

Contact your nearest sales office

www.outokumpu.com/contacts

Working towards forever.

We work with our customers and partners to create long lasting solutions for the tools of modern life and the world's most critical problems: Clean energy, clean water and efficient infrastructure. Because we believe in a world that lasts forever.

Information given in this brochure may be subject to alterations without notice. Care has been taken to ensure that the contents of this publication are accurate but Outokumpu and its affiliated companies do not accept responsibility for errors or for information which is found to be misleading. Suggestions for or descriptions of the end use or application of products or methods of working are for information only and Outokumpu and its affiliated companies accept no liability in respect thereof. Before using products supplied or manufactured by the company the customer should satisfy himself of their suitability



outokumpu.com
steelfinder.outokumpu.com